

**2112 - WEED CONTROL FABRIC**

**SECTION 2112**

**WEED CONTROL FABRIC**

**2112.1 DESCRIPTION**

This specification covers the material requirements for weed control fabric.

**2112.2 REQUIREMENTS**

Weed control fabric can be an opaque woven or non-woven material, manufactured specifically for use as a weed barrier. Use fabric that can maintain its integrity for a minimum of 2 years in direct sunlight and has the following minimum physical properties:

Weight .....	96 g/sq. yd.
Grab tensile strength .....	100 lbf.
Puncture strength .....	60 lbf.
Tear strength .....	45 lbf.

**2112.3 TEST METHODS**

Grab tensile strength .....	ASTM D 4632
Puncture strength .....	ASTM D 4786
Tear strength .....	ASTM D 4533

**2112.4 PREQUALIFICATION**

None Required.

**2112.5 BASIS OF ACCEPTANCE**

Visual inspection of the label to verify compliance with this Section.