

**KANSAS DEPARTMENT OF TRANSPORTATION  
SPECIAL PROVISION TO THE  
STANDARD SPECIFICATIONS, EDITION 2007**

**SECTION 610**

**DOUBLE ASPHALT SURFACE TREATMENT**

**Page 600-52, delete subsection 610.3l. and replace with the following:**

**l. Second Seal Coat.** If the asphalt material consists of cutback asphalt, do not apply the second seal coat until 60 days after the application of the first seal coat, unless shown otherwise in the Contract Documents.

Immediately prior to the second seal coat application, clean the surface of all foreign material, and broom to remove dust and excess cover material. Exercise care not to dislodge any cover material which is embedded in the asphalt material. Apply the second seal coat according to the provisions for the First Seal Coat in **subsections 610.3f. thru i.** Do not use brooms to shift the cover material until the initial rolling is complete, and until the asphalt material has sufficiently cured to hold the cover material. Perform any rearrangement of the cover material during the initial rolling by hand methods.

Continue rolling until the entire surface has been covered a minimum of 7 times with a pneumatic roller. Operate rollers at speeds which shall not displace the aggregate.

04-16-10 M&R (GMS)  
Jul-10 Letting