

**KANSAS DEPARTMENT OF TRANSPORTATION
SPECIAL PROVISION TO THE
STANDARD SPECIFICATIONS, EDITION 2007**

SECTION 1114

STONE FOR RIPRAP, DITCH LINING AND OTHER MISCELLANEOUS USES

Subsection 1114.1. Add to this subsection:

- Sediment Basin Risers

Subsection 1114.2. Add to this subsection:

(h) Sediment Basin Risers

(1) Quality

- Soundness, minimum 0.85
- Wear, maximum 45%
- Absorption, maximum 6.0%
- Specific Gravity (dry), minimum (by KT-6 Proc. 1) 2.20

(2) Product Control.

- Deleterious Substances. Stone for these types of construction shall be free from soapstone, shale, shale-like or other easily disintegrated material.
- Size Requirements. Provide stone for sediment basin risers that complies with **TABLE 1114-5**:

TABLE 1114-5: SEDIMENT BASIN RISERS		
Sieve Size	5 in	2 in
Percent Retained	0	90