

**KANSAS DEPARTMENT OF TRANSPORTATION
SPECIAL PROVISION TO THE
STANDARD SPECIFICATIONS, EDITION 2007**

SECTION 1402

CHEMICAL ADMIXTURES FOR CONCRETE

Page 1400-2, subsection 1402.1h. Delete this subsection and replace with the following:

h. Type S – Specific Performance Admixture. An admixture that provides a desired performance characteristic(s) other than reducing water content, or changing the time of setting of concrete, or both, without any adverse effects on the fresh, hardened, or durability properties of concrete.

Page 1400-2, subsection 1402.1i. Delete this subsection and replace with the following:

i. Type I – Plasticizing Admixture. An admixture that produces flowing concrete without further addition of water.

Page 1400-2, subsection 1402.1. Add a new subsection as follows:

j. Type II – Plasticizing and Set Retarding Admixture. An admixture that produces flowing concrete without further addition of water, and retards the setting of concrete.

NOTE: Flowing concrete is defined as having a slump equal to or greater than 7 ½ inches.

Page 1400-2, subsection 1402.2a. Delete this subsection and replace with the following:

a. Provide Type A, B, C, D, E, F, G and S admixtures that comply with ASTM C 494.

Page 1400-2, subsection 1402.3a. Delete this subsection and replace with the following:

a. Test Type A, B, C, D, E, F, G and S admixtures as specified in ASTM C 494, with the following exception:
(1) Provisional qualification, as stated in Table 1, Note C, will not be considered until at least 6 months of data has been established.