

**KANSAS DEPARTMENT OF TRANSPORTATION
SPECIAL PROVISION TO THE
STANDARD SPECIFICATIONS, EDITION 2007**

SECTION 1716

RAPID-SET CONCRETE PATCHING MATERIAL

Page 1700-25, subsection 1716.4. Delete the second paragraph and replace with the following:

If the NTPEP results comply with **subsection 1716.2** and if, after 300 freeze-thaw cycles, the laboratory test specimens exhibit no cracking, and only very slight scaling or spalling (maximum 1/8 inch depth) with no coarse aggregate visible, the name of the product will be placed on a list of prequalified products maintained by the Bureau of Materials and Research. No rapid setting concrete patch material will be used on KDOT projects unless it has been prequalified. Manufacturers are required to re-qualify at intervals stipulated by NTPEP.

04-07-08 M&R (CFN)