

**KANSAS DEPARTMENT OF TRANSPORTATION
SPECIAL PROVISION TO THE
STANDARD SPECIFICATIONS, EDITION 2007**

SECTION 2110

MULCH

Page 2100-16, subsection 2110.2. Add a new subsection:

f. Hydro-Mulch. Provide a bonded fiber matrix (BFM) product made from non-toxic, biodegradable, thermally processed, virgin, wood fibers that contains no growth or germination inhibiting factors and complies with **TABLE 2110-2:**

TABLE 2110-2: HYDRO-MULCH	
Property	Requirement
Virgin wood fibers	90% minimum
Organic matter	99% minimum
Hydrocolloid-based binder	10% minimum
“Dry” Moisture Content	9 - 15%
pH	5.5 – 7.5
Water holding capacity	13 times own weight
Dye agent color	Green or Yellow

01-07-09 M&R (CFN)
Apr-09 Letting