

**KANSAS DEPARTMENT OF TRANSPORTATION
SPECIAL PROVISION TO THE
STANDARD SPECIFICATIONS, 2015 EDITION**

SECTION 1112

**AGGREGATES FOR SURFACING OR SUBGRADE MODIFICATION
FOR COUNTY SECONDARY ROADS**

Page 1100-32, subsection 1112.2c.(1). Delete TABLE 1112-1 and replace with the following:

TABLE 1112-1: GRADATION REQUIREMENTS										
Type	Material	Percent retained On standard square mesh sieves*								Gradation Factor
		2"	1 1/2"	1"	3/4"	3/8"	No. 4	No. 8	No. 30	
SS-3	Crushed Stone		0	0-15		45-85				90-100
SS-5	Crushed Stone	0	0-5	0-30		45-90				90-100
SS-7	Sand-gravel			0	0-5	0-20				4.00 - 5.00**
SS-8	Sand-gravel			0	0-5	0-30				3.75+
SS-9	Sand-gravel			0		0-20				3.50+
SS-10	Sand-gravel	0	0-5			0-30				3.25+
SS-14	Limestone gravel		0							

*All percent retained values shall be determined using the cumulative dry mass sum of the material retained on each sieve divided by the total dry mass of the material retained on the 200 sieve after washing and sieving (KT-2) and removal of all deleterious substances
**For grading factors less than 4.00 but greater than 3.75, provide additional materials as a penalty at a rate of 1.5% for each 0.05 less than 4.00 grading factors. Use a maximum lot size of 500 cubic yards or tons to determine penalty. Average all tests within the lot to determine penalty.

Page 1100-33, subsection 1112.2c.(2). Delete TABLE 1112-2 and replace with the following:

TABLE 1112-2: DELETERIOUS SUBSTANCES					
Type	Material	Passing No. 200 sieve	Sticks (wet)	Clay Lumps & Friable Particles	Combination¹
SS-3	Crushed Stone	8.0	2.0	5.0	5.0
SS-5	Crushed Stone	8.0	2.0	5.0	5.0
SS-7	Sand-gravel	3.0	2.0	5.0	5.0
SS-8	Sand-gravel	8.0	2.0	4.0	
SS-9	Sand-gravel	10.0	2.0	3.0	
SS-10	Sand-gravel	10.0	2.0	3.0	
SS-14	Limestone gravel	7.0			

¹Of any deleterious substances except material passing No. 200.